

# **MOTIVE J185-AES**

MODEL J185-AES

VOLTAGE 12

CAPACITY 171Ah @ 20Hr MATERIAL Polypropylene

BATTERY VRLA AGM / Non-Spillable / Maintenance-Free

COLOR Maroon

WATERING No Watering Required





## **12 VOLT**

#### **PHYSICAL SPECIFICATIONS**

BCI	MODEL NAME	TERMINAL TYPE	DIMENSIONS © INCHES (mm)		WEIGHT LBS. (kg)	HANDLES	INSTALLATION ORIENTATION	
			LENGTH	WIDTH	HEIGHT F			Horizontal
921	J185-AES	M8/DT/LT	14.97 (380)	6.94 (176)	14.45 (367)	125 (57)	125 (57) Braided Rope	and Vertical

#### **ELECTRICAL SPECIFICATIONS**

VOLTAGE	CRANKING PE	ERFORMANCE	CAPACITY A MINUTES		CAPACITY <sup>B</sup> AMP-HOURS (Ah)				ENERGY (kWh)	INTERNAL RESISTANCE (m $\Omega$ )	SHORT CIRCUIT CURRENT (amps)
10	C.C.A. <sup>D</sup> @0°F	C.A. <sup>E</sup> @32°F	@ 25 Amps	@ 75 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	A E	2790
12	_	_	350	94	149	164	171	212	2.54	4.5	

#### **CHARGING INSTRUCTIONS**

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
SYSTEM VOLTAGE	12V	24V	36V	48V	
Maximum Charge Current (A)	50% of C <sub>20</sub>				
Absorption Voltage (2.40 V/cell)	14.40	28.80	43.20	57.60	
Float Voltage (2.25 V/cell)	13.50	27.00	40.50	54.00	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

#### **CHARGING TEMPERATURE COMPENSATION**

ADD	SUBTRACT
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F

### **OPERATIONAL DATA**

OPERATING TEMPERATURE	SELF DISCHARGE
-40°F to 140°F (-40°C to +60°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions

#### **RECYCLE RESPONSIBLY**









#### **STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE**

PERCENTAGE CHARGE	CELL	12 VOLT
100	2.14	12.84
75	2.09	12.54
50	2.04	12.24
25	1.99	11.94
0	1.94	11.64


#### **TROJAN J185-AES PERFORMANCE**




#### PERCENT CAPACITY VS. TEMPERATURE



#### **BATTERY DIMENSIONS** (shown with DT)



#### SELF DISCHARGE VS. TIME



#### TERMINAL TYPE



**Battery Height with Terminal in Inches (mm)** 14.45 (367) Torque Values in-lb (Nm) Connected to Stud: 95 - 105 (11 - 12) Connected to AP: 50 - 70 (6 - 8) **Bolt Size** 5/16" - 18

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are
- Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum. C.C.A. (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.
- The amount of nimities a autiety can believe when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.

  The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.
- E. C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2 CAL Clothaning Analysis are deschaled before an amperes when a reve, may regard basety or an inalitation to descend at 32 Voicel. This is sometimes referred to as marine cranting amps @ 32°F or M.C.A. @ 32°F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.

- Batteries in storage should be charged when they decline to 75% State of Charge (SOC).
- Weight may vary.













Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

